









ANTHRACITE COAL

SESUVECA

TECHNICAL SPECIFICATION

DESCRIPTION	High carbon content, slag foaming agent, carbon leveler, reducing agent, heating agent, etc.							
USE	Steelmaking, metallurgic industry, cement production, cal production, etc.							
CHEMICAL AND PHYSICAL ANALYSIS		**FC (%)**	**ASH (%)**	**VM (%)**	**FC + VM (%)**	**S (%)**	**Hu (%)**	**SIZE (mm)**	**GCV (Kcal/Kg)**
	FINE	90	6	4		0.8	1	0-3, 0-12.5	7500
		88	8	4		0.8	1	0.3, 0-12.5	7300
		80	15	5		0.8-1.0	10	0.3, 0-12.5	6700
		77	18	5		0.8-1.0	10	0.3, 0-12.5	6400
		75	20	5		0.8-1.0	10	0.3, 0-12.5	6200
		73	22	5		0.8-1.0	10	0.3, 0-12.5	5900
			15		85	0.8-1.0	10	0.3, 0-12.5	6700
			18		82	0.8-1.0	10	0.3, 0-12.5	6400
			20		80	0.8-1.0	10	0.3, 0-12.5	5900
	MEDIUM	85	11	4		0.8	6	3-6, 6-12.5, 12.5-19	7000
		82	14	4		0.8	6	3-6, 6-12.5, 12.5-19	6800
		80	16	4		0.8	6	3-6, 6-12.5, 12.5-20	6600
		78	18	4		0.8	6	3-6, 6-12.5, 12.5-21	6400
		76	20	4		0.8	6	3-6, 6-12.5, 12.5-22	6200
			20		80	0.8-1.0	6	3-6, 6-12.5, 12.5-23	6200
			18		82	0.8-1.0	6	3-6, 6-12.5, 12.5-24	6500
			15		85	0.8-1.1	6	3-6, 6-12.5, 12.5-25	6700
			12		88	0.8-1.2	8	3-6, 6-12.5, 12.5-26	7000
	GROSS	85	11	4		0.8	6	19, 0-25,4, 25,4-38, 38-50	7000
		88	8	4		0.8	6	19, 0-25,4, 25,4-38, 38-50	7300
		90	7	3		0.8	6	19, 0-25,4, 25,4-38, 38-51	7500
		92	5	3		0.8	6	19, 0-25,4, 25,4-38, 38-52	7600
PACKING	One Ton Super Bags								

FC: Fixed Carbon | VM: Volatile Matter | Ash:ASH | Hu: Moisture | S: Sulphur | GCV: Gross Calorific Value.